


PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : G03F 1/14, 1/08	A1	(11) International Publication Number: WO 94/11786 (43) International Publication Date: 26 May 1994 (26.05.94)
(21) International Application Number: PCT/US93/10709 (22) International Filing Date: 12 November 1993 (12.11.93) (30) Priority data: 07/976,782 16 November 1992 (16.11.92) US (71) Applicant: E.I. DU PONT DE NEMOURS AND COMPANY [US/US]; 1007 Market Street, Wilmington, DE 19898 (US). (72) Inventors: ALPAY, Hakki, Ufuk ; 25 Mayer Drive, Highland, NY 12528 (US). FRENCH, Roger, Harquail ; 1516 Athens Road, Wilmington, DE 19803 (US). KALK, Franklin, Road ; 8 Stoney Run Road, Wilmington, DE 19809 (US).		(74) Agents: HEISER, David, E. et al.; E.I. du Pont de Nemours and Company, Legal/Patent Records Center, 1007 Market Street, Wilmington, DE 19898 (US). (81) Designated States: JP, KR, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>

(54) Title: PHOTOMASK BLANKS**(57) Abstract**

Transmissive embedded phase shifter-photomask blanks are disclosed which comprise an optically inhomogeneous attenuating film which has a transmission of at least 0.001 and consists essentially of a combination of a metallic component and a dielectric component. One surface of the film has a higher content of metallic component than the other surface and the profile of change in extinction coefficient is gradual through the film thickness. The profile of change in extinction coefficient and the film thickness are selected to provide a phase shift of about 180° (or an odd multiple thereof) at a selected wavelength.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

TITLE

PHOTOMASK BLANKS

FIELD OF THE INVENTION

5 This invention relates to photomask blanks, and more particularly, to photomask blanks providing phase shift in incident light at a specified wavelength.

BACKGROUND OF THE INVENTION

10 Conventional photomask blanks commonly consist of a substrate, e.g., fused silica plate, on which is an opaque chrome film. Photomasks are produced from these blanks by providing a desired pattern of open areas in the film. In use, light is optically projected through the open areas of the photomask onto the surface of a
15 light sensitive substrate, such as a photopolymer-coated semiconductor wafer. Currently, photomasks are illuminated with visible or ultraviolet light. A fundamental limitation of optical imaging is that line widths of the order of the wavelength of the
20 illuminating light are diffraction limited. In other words, light having a wavelength of the same order of magnitude as the desired optical image will diffract, and the projected image will be wider than the desired image.

25 To allow for patterns narrower than the wavelength of visible or ultraviolet light to be produced, the art has considered changing to a shorter wavelength source, such as X-ray. U.S. Patent No. 4,890,309 discloses a type of attenuated (as opposed to opaque) photomask;
30 particularly useful in X-ray lithography, wherein the material and thickness of the attenuating film are selected to both pass (i.e., transmit) a fraction of the incident electromagnetic radiation and to phase shift the radiation relative to radiation passing through the
35 open features of the mask. The materials of choice are

homogeneous films of tungsten, gold, silver, alloys of these materials or alternating layers of high and low atomic number materials (e.g., tungsten and carbon).

In an effort to avoid the cost and complexity of X-ray lithography, a variety of phase-shifting photomasks have been developed for ultraviolet and visible light ranges (see, for example, B. J. Lin, SOLID STATE TECHNOLOGY, pp. 43-47, January, 1992). Among these are the rim phase-shifting photomask, which requires either substrate etching or the use of an additional phase-shifting layer. The rim phase-shifting photomask is inherently applicable to arbitrary mask patterns, but requires a large positive mask bias to reduce exposure times to a practical level and due to strong proximity effects it is difficult to delineate all feature sizes and shapes for an arbitrary mask pattern using one common exposure. An improvement over the rim phase-shifting photomask is known in the art as the attenuated phase-shifting photomask (APSPM). APSPMs employ an absorptive, partially transmitting, phase shifter in place of the conventional opaque chromium part of the patterned film. The transmission of the absorptive phase shifter is adjusted to less than about 0.20 to prevent creation of ghost lines. However, not all phase shifters can phase shift and absorb by the desired amount. Consequently, a multilayered structure consisting of materials of differing absorptive and phase shifting properties may be required in some cases. A commercially available APSPM utilizes a graded chromium oxycarbonitride composition film which varies from a Cr-N compound at the substrate-film interface to a Cr-O compound at the film-air interface, which also serves as an anti-reflective coating. While this APSPM provides a degree of phase shifting, a further procedure, such as reactive ion etching of the

substrate, in this case, fused silica, is necessary to achieve the desired 180° phase shift.

SUMMARY OF THE INVENTION

This invention provides a transmissive embedded
5 phase shifter-photomask blank (i.e., an EPS-PMB) for a
selected wavelength which comprises an optically
inhomogeneous attenuating film having a transmission of
at least 0.001 and consisting essentially of a
combination of a metallic component and a dielectric
10 component; wherein one surface of the film has a higher
content of metallic component than the other surface,
and the profile of change in the extinction coefficient
is gradual through the film thickness; and wherein said
profile of change and the film thickness are selected to
15 provide a phase shift of about 180° (or an odd multiple
thereof) at the selected wavelength.

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1. Graph of the Index of Refraction (n) and
Extinction Coefficient (k) as a function of wavelength
20 (λ) in nanometers for a representative metallic
material.

Figure 2. Graph of the Index of Refraction (n) and
Extinction Coefficient (k) as a function of wavelength
25 (λ) in nanometers for a representative dielectric
material.

Figure 3. Graph of a depth wise profile of the
index of refraction (n) as a function of distance from
substrate surface (D) in Angstroms for a graded embedded
phase shifter-photomask blank for 253 nm wavelength.

Figure 4. Graph of the optical transmission (T) as
30 a function of wavelength (λ) in nanometers for an
embedded phase shifter-photomask blank for use at
253 nm.

Figure 5. Graph of the transmitted phase shift (S)
35 as a function of wavelength (λ) in nanometers for an

embedded phase-shifter photomask blank for use at 253 nm.

Figure 6. Graph of a depth wise profile of the index of refraction (n) as a function of distance from substrate surface (D) in Angstroms for an embedded phase shifter-photomask blank for use at a wavelength of 365 nm.

Figure 7. Graph of a depth wise profile of the index of refraction (n) as a function of distance from substrate surface (D) in Angstroms for an embedded phase shifter-photomask blank for use at a wavelength of 257 nm.

DETAILED DESCRIPTION OF THE INVENTION

This invention provides an advantageous film for photomask blanks. The film provides a phase shift of about 180° (preferably $180^\circ \pm 10^\circ$) or an odd multiple thereof, for particular incident wavelengths, and is thus especially useful for producing photomasks. Normally the film is deposited on a substrate. The substrate can be any mechanically stable material which is transparent to the wavelength of incident light used. Substrates such as quartz and fused silica (glass) are preferred for availability and cost.

The films of this invention are optically inhomogeneous, in that the extinction coefficient changes through the film thickness. The optically inhomogeneous attenuating film in accordance with the instant invention is typically in the form of a continuously varying structure ranging from optically metallic characteristics at the one surface (normally a substrate-film interface) to optically dielectric characteristics at the other surface (normally a film-air interface). The metallic component (e.g., Cr-N compounds) is characterized by an extinction coefficient within the range of 0 to 6 (preferably from 0.5 to 3.5)

which generally decreases in magnitude with increasing photon energy for energy in the range from 1.5 to 6.5 eV, while the dielectric component (e.g., Cr-O compounds) is characterized by an extinction coefficient within the range of 0 to 2 (preferably from 0 to 1.5) which generally increases with increasing photon energy in the range from 1.5 to 6.5 eV. The refractive index of the metallic component is generally from 1 to 6, and is preferably from 2 to 5; and the refractive index of the dielectric component is generally from 1 to 3.5, and is preferably from 1.2 to 2.8. The metallic and dielectric components of the inhomogeneous attenuating film can be selected from materials such as transition, and non-transition, metal fluoro-oxy-carbo-nitrides. Materials which are particularly suited to the practice of this invention are metallic oxy-carbo-nitrides (i.e., M-O-C-N), metallic chloro-oxy-carbo-nitrides (i.e., M-Cl-O-C-N), metallic chloro-fluoro-oxy-carbo-nitrides (i.e., M-Cl-F-O-C-N) and metallic fluoro-oxy-carbo-nitrides (i.e., M-F-O-C-N) where M is selected from the group consisting of Cr, Fe, Mo, Zn, Co, Nb, Ta, W, Ti, Al, Mg, and Si. Cr is a preferred M; and chromium oxy-carbo-nitride is a preferred material based upon performance and availability.

The profile of the film's extinction coefficient changes gradually through the film thickness, and can vary in a smooth continuous manner or in a stepwise graded manner. For the purpose of this invention, the volume percent of the metallic and dielectric components for a given film are defined from the point in the film thickness where the extinction coefficient has a value equal to the average of the extinction coefficients of the two surfaces of the film. This "optical midpoint" position for the extinction coefficient in the film is considered for the purpose of this invention, the

effective interface between the metallic and dielectric components, even though no abrupt interface of change in the extinction coefficient may exist at that location in the film thickness. Typically, other optical properties
5 such as the index of refraction will also change gradually through the film thickness (see e.g., Figure 3).

For the purpose of this invention, the optically inhomogeneous film must have a degree of transparency
10 sufficient for the phase shift provided by the film to have the desired effect on the line width produced by the photomask. The maximum thickness of the film used in the photomask blank, d_{\max} , may be estimated in terms of index of refraction of the dielectric component of
15 the dielectric surface of the film, n_{top} , and the wavelength, λ , of light used, by:

$$d_{\max} = \frac{(m\lambda)}{(2(n_{\text{top}} - 1))}$$

where m is an odd positive integer. In practice, m is typically equal to 1 or 3, but it is not limited to
20 such, for example in the X-ray region. For a wavelength of 365 nanometers and $n_{\text{top}} = 1.5$, $d_{\max} = 365m$ nanometers. The equation is valid for the films of this invention which are not essentially opaque (i.e., the transmission of the film remains above 0.001).

25 Based on this definition of the maximum thickness, the volumes of the metallic and dielectric components can vary in thickness from essentially 0 to a thickness defined by the requirement that these inhomogeneous attenuating films have sufficient transparency.

30 Typically the metallic component is from 5 nanometers to 150 nanometers thick, and the dielectric component is from 10 nanometers to 400 nanometers thick.

An important feature of this invention is that the composition of the film can be designed in accordance

with multiple requirements that the film have the 180° phase shift required by embedded phase shifters at the desired wavelength of light employed, and that the film have the desired transmission. The film design should
5 also take into account the desired reflectivity for a particular application. Typically, desired reflectivities are within the range of from 0 to about 0.5.

For a particular pair of metallic and dielectric
10 film components such as are shown in Figure 1 and Figure 2, a generalized design may be constructed with the metallic component at one film surface (e.g., adjacent to the substrate), and the dielectric component at the
15 other film surface (e.g., adjacent to air) and a selected profile of gradual transition from metallic to dielectric as discussed above. Using the index of refraction and extinction coefficient for each of the two components, along with an estimated film thickness and a selected profile of change in optical properties,
20 one may calculate the transmission, reflectivity, and phase shift for the film. One may use the well known matrix method (see O. S. Heavens, "Optical Properties of Thin Solid Films", Dover Publications, NY, 1965, pp. 69-80 which is hereby incorporated herein by reference)
25 for these calculations. Computers may be used to perform the numerical computations. For a given profile, optimization of the film design is accomplished by calculating transmission, reflectivity and phase shift combinations within manufacturable ranges, and
30 determining which combinations provide the preferred solutions. Using computerized calculations based upon the matrix method, the profile may be modeled as a large number of thin homogeneous layers, and the characteristic matrices of all the layers are matrix
35 multiplied to calculate the reflectivity, transmission

and phase shift for the film. Predetermined optical property profiles might be used, such as linear, quadratic, cubic, exponential or gaussian. In practice the profile will be constrained by the particular
5 equipment used to manufacture the films. The equipment will also normally determine the upper and lower limits for thicknesses of regions in the film structure.

Typically the attenuating films consist essentially of from 99% to 1% by volume (as defined above),
10 preferably from 85% to 5% by volume metallic component, and from 1% to 99%, preferably from 15% to 95% dielectric component based upon the total volume of the attenuating film. Photomask blanks can be prepared by methods well known in the art. A photomask blank in
15 accordance with this invention can generally be prepared by depositing a single inhomogeneous attenuating layer on a transparent substrate in a single pass, continuous deposition process. Conventional substrates may be used as such, or may be coated with a conductive and
20 transparent film of a material such as indium oxide or stannic oxide.

The attenuating film may be deposited on a substrate by reactive sputter deposition. Reactive sputtering is a coating process that takes place in a
25 vacuum chamber. Within the vacuum chamber is a sputter chamber filled with a gas mixture comprising inert gas and reactive gas under a predetermined pressure. A target comprising the material to be sputtered is positioned in the sputter chamber on an electrically
30 conductive cathode. As a negative electrical potential is applied to the target, a plasma extending from the surface of the target is formed. The plasma comprises inert and reactive gas ions and species, and atomic units of the target. The atomic target units travel
35 through the plasma to the substrate to be coated, and

react with the reactive gas species to form various compositions. The compositions are deposited in a thin film or layer on each substrate as the substrate moves through the sputter chamber. Inert gases suitable for this process include argon, neon, krypton, and xenon. Suitable reactive gases include nitrogen, oxygen, methane and carbon dioxide. Pressure in the sputter chamber is usually in the range of 3.0×10^{-2} to 1.0×10^{-3} Torr. The target is typically chrome or a chrome-based material, such as chromium nitride, chromium carbide or chromium oxide. Further discussion of reactive sputter deposition for photomask blank production is provided in U.S. Patent Application Serial No. 07/742,245, filed August 8, 1991, which is hereby incorporated by reference.

The photomask blanks of this invention, having an inhomogeneous attenuating film, may be advantageously prepared using a reactive sputter deposition technique wherein substrates are continuously moved through a sputter chamber, by providing multiple targets (e.g., chrome-based targets) placed at intervals in the direction of movement of the substrates through the sputter chamber. By controlling the conditions within the sputter chamber (e.g., the electrical charges concurrently applied to each target, for example by direct current and/or radio frequency), the composition of the plasma over each target and the plasma overlap between targets can be adjusted to deposit onto the moving substrate a single attenuating layer having strata of different compositions and/or inter-strata transitional regions wherein the composition gradually changes from the composition of one stratum to the composition of the next resulting in an inhomogeneous attenuating layer.

This invention includes embodiments of transmissive EPS-PMBs which may be used with wavelengths within the range of 110 nm to 1000 nm.

Practice of the invention will become further
5 apparent from the following non-limiting examples.

EXAMPLE 1

Two chromium targets were positioned in a commercially available direct current planar magnetron sputtering device. Each target was about six inches
10 wide, twenty inches long and 0.25 inches high. The edge-to-edge distance between targets was about five inches. The sputter chamber was filled with a gas comprising argon, nitrogen, oxygen carbon dioxide and methane. A polished glass substrate was moved through
15 the sputter chamber under the conditions set forth in Table 1.

Table 1

Operating Pressure	2.8 x 10 ⁻³ Torr
Substrate Travel Speed	240 mm/min.
DC Elec. Power Target #1	1.4 KW
DC Elec. Power Target #2	0.85 KW
Ar	90 sccm
O ₂	3.6 sccm
N ₂	24 sccm
CH ₄	3.5 sccm
CO ₂	7.5 sccm

Under these operating conditions, due to the light emission from the different species in the two different plasmas and the plasma overlap region, a color spectrum
20 from bright blue over the first target changing to a bright pink over the second target was observed with the naked eye through windows provided on the side of the process chamber, confirming the existence of

compositional gradient within the plasma in the direction of substrate movement.

The substrates removed from the chamber had a film coating of about 87 nanometers, as determined by stylus
5 profilometry. The optical reflectivity and transmission, as well as the ellipsometric spectra of the air-film and substrate-film surfaces, were measured. Using these spectroscopic measurements, the optical
10 properties such as the index of refraction and the extinction coefficients at the air-film surface and the substrate-film surface, and also the profile of these optical properties was modeled using the matrix method described herein. The optical properties calculated for
15 the material at the substrate-film surface are shown in Figure 1 and are of a metallic nature as defined above, while the optical properties calculated for the material at the film-air surface are shown in Figure 2 and have a dielectric nature as defined above. One estimated
20 profile of the index of refraction, which is consistent with Figure 1 and Figure 2 and the measured optical and ellipsometric data was determined using the matrix method and is shown in Figure 3. While other profiles might also be consistent, the measured optical and
25 ellipsometric data cannot be interpreted assuming a film with homogeneous properties.

The transmission of the photomask blank produced is shown in Figure 4, where the transmission of the film is about 0.005 at a wavelength of 253 nm. At this
30 wavelength the phase shift of the transmitted light as determined by the matrix method is about 180° as illustrated in Figure 5. The reflectivity of this film was measured as about 0.19 at 253 nm. This photomask blank therefore is considered an embedded phase shifter photomask blank for use at 253 nm.

EXAMPLE 2

A EPS-PMB is designed for use at 365 nm. Using the metallic and dielectric components shown in Figure 1 and Figure 2, respectively, a profile suitable for an
5 EPS-PMB with a transmission of 0.027, a reflectivity of about 0.16 and 180° phase shift at 365 nm is shown in Figure 6.

EXAMPLE 3

A EPS-PMB is designed for use at 257 nm. Using the
10 metallic and dielectric components shown in Figure 1 and Figure 2, respectively, a profile suitable for an EPS-PMB with a transmission of 0.01, a reflectivity of about 0.175 and 173° phase shift at 257 nm is shown in Figure 6.

15 Example 2 and Example 3 demonstrate the inherent advantages of the inhomogeneous nature of these films and the versatility of the metallic and dielectric components of the inhomogeneous attenuating films.

Particular embodiments of the invention are
20 illustrated in the examples. Other embodiments will become apparent to those skilled in the art from a consideration of the specification or practice of the invention disclosed herein. It is understood that modifications and variations may be practiced without
25 departing from the spirit and scope of the novel concepts of this invention. It is further understood that the invention is not confined to the particular formulations and examples herein illustrated, but it embraces such modified forms thereof as come within the
30 scope of the following claims.

WHAT IS CLAIMED IS:

1. A transmissive embedded phase shifter-
photomask blank for a selected wavelength comprising an
5 optically inhomogeneous attenuating film having a
transmission of at least 0.001 and consisting
essentially of a combination of a metallic component and
a dielectric component; wherein one surface of the film
has a higher content of metallic component than the
10 other surface, and the profile of change in the
extinction coefficient is gradual through the film
thickness; and wherein said profile of change and the
film thickness are selected to provide a phase shift of
about 180°, or an odd multiple thereof, at the selected
15 wavelength.
2. The transmissive embedded phase shifter-
photomask blank of Claim 1 wherein the phase shift is
about 180°.
3. The transmissive embedded phase shifter-
20 photomask blank of Claim 2 wherein the reflectivity is
within the range of from 0 to 0.5.
4. The transmissive embedded phase shifter-
photomask blank of Claim 3 wherein the metallic
component is from 85% to 5% of the film by volume and
25 wherein the dielectric component is from 15% to 95% of
the film by volume.
5. The transmissive embedded phase shifter-
photomask blank of Claim 1, Claim 2, Claim 3, or Claim 4
wherein the selected wavelength is from 110 nm to
30 1000 nm.
6. The transmissive embedded phase shifter-
photomask blank of Claim 5 wherein the metallic
component and dielectric component are M-O-C-N
materials, M-Cl-O-C-N materials, M-Cl-F-O-C-N materials
35 or M-F-O-C-N materials where M is selected from the

group consisting of Cr, Fe, Mo, Zn, Co, Nb, Ta, W, Ti, Al, Mg, and Si.

7. The transmissive embedded phase shifter-photomask blank of Claim 6 wherein M is Cr.

5 8. The transmissive embedded phase shifter-photomask blank of Claim 7 wherein the metallic component and dielectric component are Cr-O-C-N materials.

1/4




Fig. 1




Fig. 2

2/4




Fig. 3




Fig. 4

3/4




Fig. 5




Fig. 6

4/4




Fig. 7

INTERNATIONAL SEARCH REPORT

Inter national Application No
PCT/US 93/10709A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 G03F1/14 G03F1/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 G03F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	IBM TECHNICAL DISCLOSURE BULLETIN vol. 35, no. 3, August 1992 pages 440 - 441 'Si-N Attenuated Phase Shift Layer for Phase Shift Mask Application' see the whole document ---	1-5
P,Y	US,A,5 230 971 (ALPAY) 27 July 1993 cited in the application see the whole document ---	1-8
P,Y	US,A,5 187 726 (WHITE) 16 February 1993 cited in the application see the whole document ---	1-8
-/--		

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *Z* document member of the same patent family

Date of the actual completion of the international search

24 February 1994

Date of mailing of the international search report

09.03.94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Barathe, R

INTERNATIONAL SEARCH REPORT

Inter nal Application No
PCT/US 93/10709

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	SOLID STATE TECHNOL. (USA), SOLID STATE TECHNOLOGY, JAN. 1992, USA, 35, 1, 43 - 47 ISSN 0038-111X Lin B J 'The attenuated phase-shifting mask' ----	1
A	US,A,4 890 309 (SMITH ET AL.) 26 December 1989 cited in the application see the whole document ----	1
A	PATENT ABSTRACTS OF JAPAN vol. 14, no. 565 (P-1143)17 December 1990 & JP,A,02 242 252 (TOPPAN PRINTING CO LTD) 26 September 1990 see abstract ----	1-8
A	PATENT ABSTRACTS OF JAPAN vol. 16, no. 386 (P-1404)18 August 1992 & JP,A,04 125 643 (TOPPAN PRINTING CO LTD) 27 April 1992 see abstract ----	1-8
A	EP,A,0 203 563 (ASAHI GLASS COMPANY LTD) 3 December 1986 see the whole document -----	1

INTERNATIONAL SEARCH REPORT

information on patent family members

Internal Application No

PCT/US 93/10709

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5230971	27-07-93	NONE	
US-A-5187726	16-02-93	JP-A- 5217865	27-08-93
US-A-4890309	26-12-89	NONE	
EP-A-0203563	03-12-86	JP-C- 1669770	12-06-92
		JP-A- 61272746	03-12-86
		JP-B- 63063896	08-12-88
		US-A- 4720442	19-01-88

THIS PAGE BLANK (USPTO)